

Evenex Sincro

Material Handling Guide

Evenex Sincro is an exceptionally realistic continuous low-pressure laminate CLPL supplied as 0.6mm sheets or E0 MRMDF panels. Suitable for interior joinery and furniture it is recommended for vertical use only.

- Panels do not have a melamine surface but rather a lacquered surface and therefore lower resistance to surface wear and scratching than standard laminates.
- Not recommended for outdoor use.
- Formulated primarily for dry-use areas.
- Protect from direct, bright, reflected sunlight and excessive heat, high-humidity, chemicals, water and other liquids.
- Do not drag/slide sheets across one another.
- Do not lean against walls for a prolonged period as this will cause bowing.
- Store flat at least 200mm from the floor and keep in strapped pack covered with plastic sheeting and/or a cover sheet and protected from light and humidity until ready to use. Keep the humidity range of the storage area between 40% and 70% (RH).
- Avoid applying adhesive tapes to the face & back of panels as many contain solvents which will affect the material. Heat and a prolonged period of the tape being on the face can also increase the chance of damaging the surface. Should tape need to be used, refer to the Adhesive Tape Report on TESA 4308 tape which can be found at eltongroup.com/downloads.
- It is recommended that handles or push plates be installed on Evenex Sincro faced doors as pressure from repetitive handling may over time damage surfaces due to abrasion from the transfer of oil, dirt and other materials. Push to open door mechanisms are not recommended without dedicated push plates.
- Use either a soft dry cloth or feather duster to remove surface dust. If dust accumulation is heavy, the surface may be lightly vacuumed.
- Clean with a damp, non-abrasive cloth and warm soapy water. Do not allow to become excessively wet. Dry with a soft cloth.
- Do not use microfibre cloths for general cleaning, as they are abrasive and will gradually wear down the surface finish.
- Do not use harsh cleaners, solvents or chemicals. If you do want to try a chemical, please perform a stain-resistance test on an off-cut first.

For further information and *Terms and Conditions* please refer to eltongroup.com/evenex-sincro

