

### Material Handling Guide

- Evenex is a continuous low-pressure laminate pressed and stocked in 2400mm & 3000mm x 1200mm on 18mm, 25mm or 32mm E0 MRMDF board. The standard thickness of the face laminate is 0.2mm. Other sizes & substrates are available on request.
- Evenex panels do not have a melamine surface but rather a lacquered surface and therefore lower resistance to surface wear and scratching than standard laminates.
- Evenex is recommended for vertical and light horizontal use only.
- DO NOT drag/slide sheets across one another.
- Stack panels onto a flat surface, avoid leaning against walls for a prolonged period to reduce the chance of bowing.
- Evenex is not recommended for outdoor use.
- Clean with a damp, non-abrasive cloth and warm soapy water. DO NOT use harsh chemicals. If you do want to try a chemical, please do so on an off-cut.
- AVOID applying adhesive tapes to the face & back of the Evenex panels as many contain solvents which will affect the material. Heat and a prolonged period of the tape being on the face can also increase the chance of damaging the surface. Should tape need to be used, refer to the Adhesive Tape Report on TESA 4308 tape which can be found at [eltongroup.com/evenex](http://eltongroup.com/evenex) under [Downloads](#).
- Should you have any further queries or questions about Evenex, please contact Elton Group directly on 03 8555 2235

