

Evenex

Material Handling Guide

- Evenex is a continuous low-pressure laminate pressed and stocked in 2400mm & 3000mm x 1200mm on 18mm, 25mm or 32mm E0 MRMDF board. The standard thickness of the face laminate is 0.2mm. Other sizes & substrates are available on request.
- Evenex panels do not have a melamine surface but rather a lacquered surface and therefore lower resistance to surface wear and scratching than standard laminates.
- Evenex is recommended for vertical and light horizontal use only.
- DO NOT drag/slide sheets across one another.
- Stack panels onto a flat surface, avoid leaning against walls for a prolonged period to reduce the chance of bowing.
- Evenex is not recommended for outdoor use.
- Clean with a damp, non-abrasive cloth and warm soapy water. DO NOT use harsh chemicals. If you do want to try a chemical, please do so on an off-cut.
- AVOID applying adhesive tapes to the face & back of the Evenex panels as many contain solvents which will affect the material. Heat and a prolonged period of the tape being on the face can also increase the chance of damaging the surface. Should tape need to be used, refer to the Adhesive Tape Report on TESA 4308 tape which can be found at eltongroup.com/evenex under [Downloads](#).
- It is recommended that handles or push plates be installed on Evenex faced doors as pressure from repetitive handling may over time damage surfaces due to abrasion from the transfer of oil, dirt and other materials. Push to open door mechanisms are not recommended without dedicated push plates.
- Finger or hand marks will show less on mid-toned finishes compared to dark toned finishes.
- For further information and Terms and Conditions please call us on 1300 133 481 or refer to our website eltongroup.com/evenex

